



Leather, perfected.

Outlaw

LEATHER GOODS

MARROQUINERÍA

 Bovine Leather

 Thickness 1.6 – 2.0 mm.

 Average Size ?? sqft.

 Vegetable Tanned

 Double Shoulder

 USA origin

A tribute to freedom and resilience, Outlaw is our most vibrant and audacious vegetable-tanned leather. Its wild marbling and deep, rich tones reflect the spirit of the untamed. Perfect for standout saddlery, statement upholstery, or premium leather goods that demand

Un tributo a la libertad y la resiliencia, Outlaw es nuestro cuero curtido vegetal más vibrante y audaz. Su marmoleado salvaje y sus tonos profundos y ricos reflejan el espíritu indomable. Perfecto para talabartería destacada, tapicería con carácter o artículos de piel premium que buscan robar miradas.

CRUST INSPECTION OUTPUT APT TO VEG / INSEPCCIÓN CRUST SALIDA APT A VEG

Characteristic Cracterística	Specification Especificación	Sample Size Tamaño de muestra	Inspection Method Método de Inspección
Selection Selección	A/B	100%	Visual, see ESACC002 Visual, ver ESACC002
Caliber Calibre	2.3 +/- 0.1 mm	100%	Check thickness according to leather section, see INCCA027 (Flat gauge) and record average range Revisar calibre según parte del cuero, ver documento INCCA027 (Calibrador PLANO y registrar rango promedio)

CRUST INSPECTION INPUT TO ACS / CRUST INSEPCCIÓN DE ENTRADA A ACS

Caliber Calibre	2.1 +/- 0.1 mm	100%	Check thickness according to leather section, see INCCA027 (Flat gauge) and record average range Revisar calibre según parte del cuero, ver documento INCCA027 (Calibrador PLANO y registrar rango promedio)
Contamination Contaminación	No visible foreign matter No se debe ver basura	100%	Visual inspection table Mesa de inspección (visual)
Grain Break Ruptura de Flor	Avoid grain break Evitar ruptura de flor	10% random 10% aleatorio	Perform manual grain break test Hacer prueba de ruptura de flor manual
Moisture Content Humedad	8 - 15 %	10% random 10% aleatorio	CIA800
Buffing Pulido	Buffed on grain and flesh side Pulido por flor y carne	100%	Visual, uniform Visual, uniforme

FINISHED LEATHER INSPECTION / INSEPCCIÓN DEL ACABADO

Apparence (gloss, color, embossing) Apariencia (brillo, color, grabado)	Uniform Uniforme	100%	As per approved master Ver máster
Caliber Calibre	1.8 +/- 0.2 mm	100%	Check thickness according to leather section, see INCCA027 (Round gauge) and record average range Revisar calibre según parte del cuero, ver documento INCCA027 (Calibrador redondo y registrar rango promedio)
Break (crack effect) Quiebre	Max. 3 (break scale) 3 max en quiebre	10% random 10% aleatorio	See (ESAC009) SATRA Std. 174 scale Ver (ESAC009) Escala SATRA Std. 174

FINISHED LEATHER, LABORATORY TESTING / INSEPCCIÓN ACABADO LABORATORIO

Grain Break Ruptura de Flor	Minimum 20 Mínimo 20	1 specimen, 3 x 12 cm 1 probeta, 3x12 cm	Perform grain break test according to leather testing manual (Clave P-050). Use apparatus for grain cracking test Hacer prueba de ruptura de flor en base al manual de técnicas de analisis (Clave P-050). Utilizar aparato para ruptura de flor .
--------------------------------	-------------------------	---	---



Our ISO 9001 certification ensures every stage of production follows strict, standardized processes—delivering consistent quality, reliable performance, and confidence you can trust in every batch.

We operate with 100% solar energy and prioritize the environment by treating all water used while continuously refining our processes to reduce consumption responsible waste management focused on circularity.